



Covinax 169-00

PRODUCT DESCRIPTION

Covinax 169-00 is a polyvinyl alcohol stabilized vinyl acrylic copolymer emulsion developed for a variety of permanent pressure sensitive applications requiring very aggressive tack. It exhibits outstanding adhesion to most synthetic films, including treated and untreated polyethylene and polypropylene, tyvek and cryovac. It performs well in low temperatures and is widely used in packaging applications both formulated and as a straight polymer. Covinax 169-00 can be formulated into a wash-away adhesive by the addition of a nonionic surfactant. The polyvinyl alcohol colloid allows easy cleanup and imparts excellent machining. It can be applied with a knife, rod, roller coater or extruded in beads for various packaging applications. Covinax 169-00 is FDA compliant under 21CFR 175.105, 21CFR 176.180.

PHYSICAL PROPERTIES

Polymer Type:	Vinyl acrylic	Freeze/Thaw Stability:	Unstable
Protective System:	Polyvinyl alcohol	Weight Per Gallon:	8.5
Viscosity (cps):	1600-3400 (LVF, Spindle #2/60 RPM/77° F)	Color:	White
Percent Solids:	58.0 – 60.00	Shelf Life:	3 months
pH:	4.50 – 5.50		
Glass Transition Temperature (T_g):(DSC):	-42.8 °C		
	(DMA): -23.1 °C		

PERFORMANCE PROPERTIES

A 1 mil (28g/M²) dry film of Covinax 169-00 cast directly onto 1 mil thickness polyester film will exhibit the following average performance properties when tested on #304 stainless steel, which has a #3 surface finish.

Test	Typical Values	Specification Range
180° Peel Adhesion ¹ (lbs)	3.20	3.0 minimum
178° Shear Adhesion ² (minutes)	27	5 minimum
Loop Tack ³ (lbs)	3.60	2.5 minimum

FDA Compliance: 21CFR 175.105
21CFR 176.180

¹ Franklin International 03QC5002, 30 minute dwell.

² Franklin International 03QC5003, 0.25 square inch, 500 gram load, 10 minute dwell.

³ Franklin International 03QC5004, 1 square inch contact, 1 second dwell.

**Covinax 169-00****AVERAGE APPLICATION PROPERTIES**

TEST/SUBSTRATE	Facestock: Paper				Facestock: BOPP Film			
	LDPE	HDPE	Vinyl	Corrugate	LDPE	HDPE	Vinyl	Corrugate
180° peel (lb/lineal inch width) 30 minute dwell	PT	PT	PT	PT	3.54C	3.65C	3.78C	PT
90° peel (lb/lineal inch width) 30 minute dwell	2.10A	2.36A	6.00T	1.54A	1.58A	1.66A	4.92A	1.44A
Loop Tack (lb)	2.91	4.32	6.46	3.14	1.55	3.55	4.65	1.50

	Facestock: Paper	Facestock: BOPP Film	Facestock: Mylar
178° Shear (500 g, 0.25 in ²) (minutes)	27C	34C	27C
SAFT Testing (min/temp °C)	39/62.3 °C	27.3/62.3 °C	31.3/66.3 °C
Substrate: Stainless Steel		Coat weight: 1.0 mil (+/-0.1 mil)	

C = Cohesive A = Adhesive PT = Paper Tear FP = Fiber pick

ADDITIONAL INFORMATION**Yellowing (Colorimeter "b" value)**

UV Exposure (1 week) Mylar		Heat Exposure (1 week @ 140° F) Paper	
Before	After	Before	After
4.64	7.02	2.60	4.35

The data provided in this Product Data Sheet represents typical physical and/or performance values for the product under a given set of testing conditions. The ranges or values are not specifications. Specifications are set based on statistical analysis of measurements made by the quality control laboratory on production material and will accurately reflect production capabilities. This data should be used as a guide for product selection only.

Important Notice to Purchaser: Our recommendations, if any, for use of this product are based on tests believed to be reliable. The greatest care is exercised in the selection of our materials and in our manufacturing operations. However, we make no recommendation to use this product in any manner which conflicts with existing laws and/or patents and WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, REGARDING THIS PRODUCT OR ITS USE, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE, THE MANUFACTURER IS NOT LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL OR SPECIAL DAMAGES OF ANY KIND. Revised 07/14/08.

©Copyright 2008. All rights reserved. Franklin International.