



Micronax 240-00

PRODUCT DESCRIPTION

Micronax 240-00 is a water based pressure sensitive adhesive that utilizes microsphere technology. This ultra removable, permanently repositionable product offers good quick stick to a wide variety of substrates. Micronax 240-00 can be applied repeatedly without loss of its initial quick stick. Micronax 240-00 is primarily used in repositionable applications, i.e., notes, wall borders, protective masking, memo pads and other applications requiring multiple application and removal cycles. The development of performance properties is highly dependent on the amount of adhesive applied. A typical coating weight of 6-8 lbs/ream is suggested as a starting point. Micronax 240-00 is designed for direct coating via Mayer rod or gravure methods.

TRANSFER COATING IS NOT APPROPRIATE FOR THIS TECHNOLOGY. AGITATE AT MODERATE SPEED BEFORE USE.

Micronax 240-00 is FDA compliant under 21CFR 175.105 and 21CFR 176.180.

PHYSICAL PROPERTIES

Polymer Type:	Acrylic	Freeze/Thaw Stability:	Unstable
Protective System:	Alcohol and surfactant stabilized	Weight Per Gallon:	8.30
Viscosity (cps):	350 Max (RVF, Spindle #2/50 RPM/77°F)	Color:	White
Percent Solids:	30.0 -34.0	Shelf Life:	6 months
pH:	7.90 – 9.50		
Glass Transition Temperature (T_g): (DSC):	-71.0°C		
	(DMA): -55.9°C		

PERFORMANCE PROPERTIES

A 1/2 mil (14g/M²) dry film of Micronax 240-00 cast directly onto 1 mil thickness polyester film will exhibit the following average performance properties when tested on #304 stainless steel, which has a #3 surface finish.

Test	Typical Values	Specification Range
180° Peel Adhesion ¹ (gms)	113	340.5gm (0.75lbs) maximum
Loop Tack ² (gms)	181	408.6gm (0.90lbs) maximum

FDA Compliance: 21CFR 175.105
21CFR 176.180

¹ Franklin International 03QC5002, 30 minute dwell.

² Franklin International 03QC5004, 1 square inch contact, 1 second dwell.

**Micronax 240-00****AVERAGE APPLICATION PROPERTIES**

TEST/SUBSTRATE	Facestock: Paper				Facestock: BOPP Film			
	LDPE	HDPE	Vinyl	Corrugate	LDPE	HDPE	Vinyl	Corrugate
180° peel (gm/lineal inch width) 30 minute dwell	20.9A	14.5A	116.7A	20.9A	19.5A	62.7A	172.5A	65.4A
90° peel (gm/lineal inch width) 30 minute dwell	41.4A	35.8A	103.6A	28.0A	168.0A	177.1A	236.1A	172.5A
Loop Tack (gms)	104.4	113.5	158.9	40.9	168.0	177.1	236.1	172.5

	Facestock: Paper	Facestock: BOPP Film	Facestock: Mylar
SAFT Testing (min/temp° C)	7/30° C	4/26° C	4/28° C
Substrate: Stainless Steel		Coat weight: 0.5 mil (+/-0.1 mil)	

C = Cohesive

A = Adhesive

PT = Paper Tear

FP = Fiber pick

ADDITIONAL INFORMATION**Yellowing (Colorimeter "b" value)**

UV Exposure (1 week) Mylar		Heat Exposure (1 week @ 140° F) Paper	
Before	After	Before	After
0.87	3.01	-1.04	2.67

The data provided in this Product Data Sheet represents typical physical and/or performance values for the product under a given set of testing conditions. The ranges or values are not specifications. Specifications are set based on statistical analysis of measurements made by the quality control laboratory on production material and will accurately reflect production capabilities. This data should be used as a guide for product selection only.

Important Notice to Purchaser: Our recommendations, if any, for use of this product are based on tests believed to be reliable. The greatest care is exercised in the selection of our materials and in our manufacturing operations. However, we make no recommendation to use this product in any manner which conflicts with existing laws and/or patents and WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, REGARDING THIS PRODUCT OR ITS USE, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE, THE MANUFACTURER IS NOT LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL OR SPECIAL DAMAGES OF ANY KIND. Revised 11/13/11.

©Copyright 2011. All rights reserved. Franklin International.